


# LEAD ACID (AGM) BATTERY

## MD-32 Premium

by EXIDE

### TECHNICAL DATA SHEET FOR MD- 32 Premium (12V 32AH) VRLA BATTERY



#### CONSTRUCTION:

- Positive and negative plates in lead-tin-calcium alloy.
- Separator - low resistance micro porous glass fiber.
- The electrolyte is absorbed within this material, preventing acid leakage in case of accidental damage.
- Terminals with a large surface area provide maximum conductivity.
- Self-regulating pressure relief valve.
- 100% ensured capacity (through Data-logger) during manufacturing.
- Stronger, sturdier & attractive packaging.
- Especially suited for UPS & Power Application

#### FEATURES: -




- International Size.
- Free from Orientation Constraints.
- Eco-Friendly.
- Easy Handling.
- Ready to Use.
- Long Service Life.
- Low Self-discharge.
- Excellent Charge retention & recovering ability.
- Superior High Rate Discharge.
- High Reliability.

#### Performance Characteristics confirming to JISC8702

Battery Type	Nominal Voltage (V)	Rated Capacity (Ah) at 27°C						Dimensions (mm)			Weight (Kg) (±5%)	
		20 hr 1.75V/ cell	10 hr 1.75V/ cell	3 hr 1.7 V/ cell	1.5 hr 1.7V/ cell	1 hr 1.6V/ cell	30min 1.6V/ cell	Overall Height up to lid top ±2	Height up to lid top ±2	Length ±1		
MD-32	12	32	29.1	24.0	23.0	19.2	16	179.0	179.0	178.0	124.0	9.9

#### NOTES ON OPERATION





Mode of Operation	Voltage setting per 12V unit for ambience Temp. 20 -30 °C	Current setting
FLOAT	13.7V ± 0.1V	Maximum :0.3CA Minimum: 0.1CA
BOOST	14.1V ± 0.1V	
CYCLE	14.7V ± 0.1V	



Constant Power Discharge Rating in Watts per Battery for POWERSAFE PLUS @27°C							
	Ah	10 min	15 min	20 min	30 min	45 min	60 min
Watt/Battery @ 1.7 0V	32Ah	777	612	498	369	254	249
Watt/Battery @ 1.7 5V		752	590	482	357	249	244
Watt/Battery @ 1.80V		728	567	467	346	244	239

#### Discharge Current & Recommended Final Discharge Voltage

Discharge Current (A)	Final Discharge Voltage(V/Cell)
0.2 C > (A) or intermittent discharge	1.75
0.2 C< or = (A) < 0.5 C	1.70
0.5 C< or = (A) < 1.0 C	1.55
1.0 C< or = (A)	1.30



#### Product Details

AH Efficiency	>90%
WH Efficiency	>80%
Internal Resistance	10 mΩ max @ full charge 27°C
Operating Temperature Range	0°C to 45°C
Self-Discharge/Month @ 27 ° C	<3% of Rated Capacity
Recommended period of storage	3 months from the date of dispatch and to be stored in a covered place at 27°C
Material of container	ABS (FR Grade Optional)
Type of +ve &-ve plate	Flat Pasted
Recommended Terminal Torque	2.5 N·m

END VOLTAGE/ CELL	TEMP(C)	DISCHARGE TIME												
		10min	15min	20min	30min	1 hrs	1.5 hrs	2 hrs	3 hrs	4 hrs	5 hrs	6 hrs	8 hrs	10 hrs
1.80	25	2.0C	1.65C	1.4C	1.1C	0.64C	0.42C	0.36C	0.27C	0.210C	0.17C	0.145C	0.11C	0.090C
	5	1.65C	1.3C	1.1C	0.95C	0.59C	0.34C	0.29C	0.230C	0.182C	0.147C	0.129C	0.098C	0.080C
	-5	1.3C	1.0C	0.86C	0.76C	0.48C	0.28C	0.24C	0.198C	0.154C	0.125C	0.115C	0.087C	0.071C
1.75	25	2.15C	1.72C	1.45C	1.12C	0.65C	0.45C	0.38C	0.28C	0.22C	0.180C	0.15C	0.12C	0.099C
	5	1.72C	1.40C	1.15C	0.97C	0.60C	0.36C	0.30C	0.24C	0.190C	0.150C	0.130C	0.100C	0.088C
	-5	1.45C	1.10C	0.93C	0.81C	0.50C	0.30C	0.25C	0.20C	0.160C	0.130C	0.119C	0.090C	0.078C
1.70	25	2.3C	1.8C	1.5C	1.15C	0.67C	0.48C	0.40C	0.29C	0.230C	0.19C	0.165C	0.13C	0.108C
	5	1.8C	1.5C	1.2C	1.0C	0.62C	0.39C	0.32C	0.250C	0.199C	0.164C	0.143C	0.116C	0.096C
	-5	1.6C	1.2C	1.0C	0.86C	0.53C	0.32C	0.27C	0.213C	0.168C	0.139C	0.123C	0.103C	0.086C
1.65	25	2.35C	1.85C	1.55C	1.2C	0.69C	0.50C	0.41C	0.300C	0.240C	0.200C	0.170C	0.135C	0.110C
	5	1.9C	1.6C	1.3C	1.05C	0.64C	0.40C	0.33C	0.260C	0.208C	0.173C	0.147C	0.120C	0.098C
	-5	1.6C	1.25C	1.05C	0.88C	0.54C	0.34C	0.27C	0.220C	0.176C	0.147C	0.125C	0.107C	0.087C
1.60	25	2.4C	1.9C	1.6C	1.25C	0.7C	0.51C	0.42C	0.310C	0.250C	0.210C	0.180C	0.140C	0.115C
	5	2.0C	1.7C	1.4C	1.10C	0.66C	0.41C	0.34C	0.270C	0.216C	0.182C	0.156C	0.125C	0.102C
	-5	1.65C	1.3C	1.1C	0.9C	0.55C	0.34C	0.28C	0.227C	0.183C	0.154C	0.132C	0.111C	0.091C

Note: C represents the C20 rated capacity

