

Electric Vehicle Battery (Graphene)

6-DZF-24.9

Applications

- > Electric vehicle
- > Electric wheelchair
- > Electric scooter
- > Electric play car for children
-) Garbage truck
- > Patrol car


General Features

- High Corrosion Resistant Performance: Pb-Ca multi-alloy grid
- High Energy Density and Power Density
- > Excellent Charge Acceptance Ability
- > Strong High and Low Temperature Performance
- Optimized Capability of instant High-current Discharging
- Low self-discharge rate



Dimension: $181(L)\times77(W)\times170(H)\times170(TH)$ Unit: mm









Terminal

Electric Vehicle Battery (Graphene) 6-DZF-24.9 (30Ah) 12V30AH@C20 Keep out of reach of children Don't adjoint-circuit battery terminals Boo't disassemble drop, asverte mechanical shock Made in China

Specification

Nominal Voltage	12V						
Nominal Capacity	24.9Ah						
Design life	5 years						
Terminal	M5						
Approx. Weight	Approx7.00kg (15.47lbs)						
Container Material	terial ABS						
	30.0Ah 20Hour Rate (1.50A to 10.5V)						
Rated Capacity	28.0Ah 10Hour Rate (2.80A to 10.5V)						
	24.9Ah 3Hour Rate (8.30A to 10.5V)						

Discharge: -20 ~50℃(-4~ 122°F)

Operating Temperature

Charge: -20 ~50℃(-4~ 122°F)

Storage: -20 ~50℃(-4~ 122°F)

Float Use:13.7-13.9V@25℃

Float Use:13.7-13.9V@25°C

Charge Method
(25°C)


Cycle Use:14.7-14.9V,@25°C

Max charge current 4.0A


Self discharge 3% of capacity declined per month at 25°C

Constan	it Current	Discharge	e Charact	eristics	Unit: A (25	5℃, 77 ℉)				
FV/Time	5min	15min	30min	1h	2h	3h	5h	8h	10h	20h
1.60V	110.1	59.0	36.0	20.6	12.31	8.48	5.14	3.30	2.67	1.529
1.65V	107.0	57.3	35.4	20.5	12.21	8.39	5.11	3.28	2.64	1.519
1.70V	102.9	56.0	34.8	20.4	12.10	8.28	5.03	3.23	2.63	1.510
1.75V	94.3	54.2	34.4	20.0	12.00	8.20	5.00	3.21	2.60	1.500
1.80V	84.5	50.4	32.9	19.5	11.79	8.15	4.88	3.13	2.56	1.490
1.85V	75.4	45.2	30.1	18.1	11.17	7.67	4.62	2.96	2.49	1.462
Consta	nt Power	Dischar	de Chara	cteristic	s Unit: V	V/cell(25	℃, 77 ℉)			
			,							
FV/Time	5min	15min	30min	1h	2h	3h	5h	8h	10h	20h
FV/Time 1.60V									10h 4.66	20h 2.73
	5min	15min	30min	1h	2h	3h	5h	8h		
1.60V	5min 167.1	15min 94.6	30min 59.0	1h 35.4	2h 21.2	3h 14.64	5h 8.85	8h 5.83	4.66	2.73
1.60V 1.65V	5min 167.1 161.0	15min 94.6 92.6	30min 59.0 58.6	1h 35.4 35.0	2h 21.2 21.2	3h 14.64 14.44	5h 8.85 8.82	8h 5.83 5.77	4.66 4.64	2.73 2.72
1.60V 1.65V 1.70V	5min 167.1 161.0 160.0	15min 94.6 92.6 91.8	30min 59.0 58.6 58.5	1h 35.4 35.0 34.8	2h 21.2 21.2 21.1	3h 14.64 14.44 14.35	5h 8.85 8.82 8.75	8h 5.83 5.77 5.68	4.66 4.64 4.57	2.73 2.72 2.70


Discharge characteristic




Charging characteristic




The effect of temperature on capacity



The effect of discharge depth on cycle life



Curves of self-discharge



Curves of open circuit voltage vs. capacity

